

Amendments to the Claims:

The listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) In a laminated glass having an interlayer film between at least two transparent glass platy bodies,

the laminated glass being characterized in that functional ultra-fine particles of a particle diameter of not greater than 0.2 μ m are dispersed in the interlayer film,

that the functional ultra-fine particles comprise a single substance of metal, oxide, nitride, sulfide or Sb- or F-doped substance of Sn, Ti, Si, Zn, Zr, Fe, Al, Cr, Co, Ce, In, Ni, Ag, Cu, Pt, Mn, Ta, W, V ~~and~~ or Mo, or a composite selected from at least two of these, or a mixture containing an organic resin substance in the single substance or composite, or a coated substance coated with the single substance or composite, or an antimony-doped tin oxide and/or tin-doped indium oxide, ~~and~~

~~that an infrared-reflective film that is a single layer and an alternately laminated one of a metal, oxide or nitride having absorption and reflection in infrared region and has a sheet resistivity ranging from 1k Ω /□ to 10G Ω /□ is formed on at least one surface of the interlayer film, and~~

that the infrared-reflective film is (a) a single layer made of a metal, oxide or nitride having absorption and reflection in an infrared region, or (b) a laminate of five layers or less, each layer of the laminate being independently made of a metal, oxide, or nitride having absorption and reflection in an infrared region.

2. (Currently Amended) In a laminated glass having an interlayer film between at least two transparent glass platy bodies,

the laminated glass being characterized in that an infrared-reflective film ~~that is a single layer and an alternately laminated one of a metal, oxide or nitride having absorption and reflection in infrared region~~ and has a sheet resistivity ranging from $1\text{k}\Omega/\square$ to $10\text{G}\Omega/\square$ is formed on at least one transparent glass platy body constituting the laminated glass,

that the infrared-reflective films is (a) a single layer made of a metal, oxide or nitride having absorption and reflection in an infrared region, or (b) a laminate of five layers or less, each layer of the laminate being independently made of a metal, oxide or nitride having absorption and reflection in an infrared region, and

that functional ultra-fine particles of a particle diameter of not greater than $0.2\mu\text{m}$ are dispersed in the interlayer film, that the functional ultra-fine particles comprise a single substance of metal, oxide, nitride, sulfide or Sb- or F-doped substance of Sn, Ti, Si, Zn, Zr, Fe, Al, Cr, Co, Ce, In, Ni, Ag, Cu, Pt, Mn, Ta, W, V ~~and~~ or Mo, or a composite selected from at least two of these, or a mixture containing an organic resin substance in the single substance or composite, or a coated substance coated with the single substance or composite, or an antimony-doped tin oxide and/or tin-doped indium oxide.

3-4. (Canceled)

5. (Previously Presented) A laminated glass according to claim 1, which is characterized in that the infrared ray reflective film has a sheet resistivity value of not less than $1\text{k}\Omega/\square$, and which is used for an architectural window.

6. (Previously Presented) A laminated glass according to claim 1, which is characterized in that the infrared ray reflective film has a sheet resistivity value of not less than $20\text{k}\Omega/\square$, and which is used for a vehicular window.

7. (Previously Presented) A laminated glass according to claim 2, which is characterized in that the infrared ray reflective film has a sheet resistivity value of not less than $1\text{k}\Omega/\square$, and which is used for an architectural window.

8. (Previously Presented) A laminated glass according to claim 2, which is characterized in that the infrared ray reflective film has a sheet resistivity value of not less than $20\text{k}\Omega/\square$, and which is used for a vehicular window.

9. (New) A laminated glass according to claim 1, wherein the infrared-reflective film is the single layer or a laminate of three layers, each layer of the laminate being independently made of a metal, oxide, or nitride having absorption and reflection in an infrared region.

10. (New) A laminated glass according to claim 2, wherein the infrared-reflective film is the single layer or a laminate of three layers, each layer of the laminate being independently made of a metal, oxide, or nitride having absorption and reflection in an infrared region.

11. (New) A laminated glass according to claim 1, wherein the infrared-reflective film is (a) a single layer made of a metal oxide having absorption and reflection in an infrared region, or (b) a laminate of three layers, (i) a first layer of the laminate being formed on the at least one surface of the interlayer film and being made of a metal oxide or metal nitride, (ii) a second layer of the laminate being formed on the first layer and being made of a metal, metal nitride, or metal oxide, (iii) a third layer of the laminate being formed on the second layer and being made of a metal oxide or metal nitride.

12. (New) A laminated glass according to claim 2, wherein the infrared-reflective film is (a) a single layer made of a metal oxide having absorption and

reflection in an infrared region, or (b) a laminate of three layers, (i) a first layer of the laminate being formed on the at least one transparent glass platy body and being made of a metal oxide or metal nitride, (ii) a second layer of the laminate being formed on the first layer and being made of a metal, metal nitride, or metal oxide, (iii) a third layer of the laminate being formed on the second layer and being made of a metal oxide or metal nitride.

13. (New) A laminated glass according to claim 1, wherein the infrared-reflective film is (a) a single layer made of CrO, NiCrO or a stainless steel oxide, or (b) a laminate of three layers, (i) a first layer of the laminate being formed on the at least one surface of the interlayer film and being made of ZnO, SnO, SiO or Si₃N₄, (ii) a second layer of the laminate being formed on the first layer and being made of a stainless steel, a stainless steel nitride, CrN, Si, TiO, or TiN, (iii) a third layer of the laminate being formed on the second layer and being made of ZnO, SnO, SiO, or TiN.

14. (New) A laminated glass according to claim 2, wherein the infrared-reflective film is (a) a single layer made of CrO, NiCrO or a stainless steel oxide, or (b) a laminate of three layers, (i) a first layer of the laminate being formed on the at least one transparent glass platy body and being made of ZnO, SnO, SiO or TiN, (ii) a second layer of the laminate being formed on the first layer and being made of a stainless steel, a stainless steel nitride, CrN, Si, TiO, or TiN, (iii) a third layer of the laminate being formed on the second layer and being made of ZnO, SnO, SiO, or Si₃N₄.

15. (New) A laminated glass according to claim 1, wherein the infrared-reflective film is (a) a single layer made of CrO, NiCrO or a stainless steel oxide, or (b) a laminate of three layers having a first layer formed on the at least one surface of the interlayer film, a second layer formed on the first layer, and a third layer formed on the second layer, the first, second and third layers of the

laminate respectively being (i) ZnO, a stainless steel and ZnO, (ii) ZnO, a stainless steel nitride and ZnO, (iii) ZnO, CrN and ZnO, (iv) SnO, CrN and SnO, (v) SiO, Si and SiO, (vi) Si₃N₄, TiO and TiN, or (vii) ZnO, TiN and ZnO.

16. (New) A laminated glass according to claim 2, wherein the infrared-reflective film is (a) a single layer made of CrO, NiCrO or a stainless steel oxide, or (b) a laminate of three layers having a first layer formed on the at least one transparent glass platy body, a second layer formed on the first layer, and a third layer formed on the second layer, the first, second and third layers of the laminate respectively being (i) ZnO, a stainless steel and ZnO, (ii) ZnO, a stainless steel nitride and ZnO, (iii) ZnO, CrN and ZnO, (iv) SnO, CrN and SnO, (v) SiO, Si and SiO, (vi) TiN, TiO and Si₃N₄, or (vii) ZnO, TiN and ZnO.

17. (New) A laminated glass according to claim 1, wherein the infrared-reflective film is a laminate of five layers, (i) a first layer of the laminate being formed on the at least one surface of the interlayer film and being made of ZnO, (ii) a second layer of the laminate being formed on the first layer and being made of TiN, (iii) a third layer of the laminate being formed on the second layer and being made of ZnO, (iv) a fourth layer of the laminate being formed on the third layer and being made of TiN, and (v) a fifth layer of the laminate being formed on the fourth layer and being made of ZnO.

18. (New) A laminated glass according to claim 2, wherein the infrared-reflective film is a laminate of five layers, (i) a first layer of the laminate being formed on the at least one transparent glass platy body and being made of ZnO, (ii) a second layer of the laminate being formed on the first layer and being made of TiN, (iii) a third layer of the laminate being formed on the second layer and being made of ZnO, (iv) a fourth layer of the laminate being formed on the third layer and being made of TiN, and (v) a fifth layer of the laminate being formed on the fourth layer and being made of ZnO.

19. (New) A laminated glass according to claim 1, wherein the functional ultra-fine particles consist of a single substance of metal, oxide, nitride, sulfide, or Sb- or F-doped substance of Sn, Ti, Si, Zn, Zr, Fe, Al, Cr, Co, Ce, In, Ni, Ag, Cu, Pt, Mn, Ta, W, V or Mo, or a composite selected from at least two of these, or a mixture containing an organic resin substance in the single substance or composite, or a coated substance coated with the single substance or composite, or an antimony-doped tin oxide and/or tin-doped indium oxide.

20. (New) A laminated glass according to claim 2, wherein the functional ultra-fine particles consist of a single substance of metal, oxide, nitride, sulfide, or Sb- or F-doped substance of Sn, Ti, Si, Zn, Zr, Fe, Al, Cr, Co, Ce, In, Ni, Ag, Cu, Pt, Mn, Ta, W, V or Mo, or a composite selected from at least two of these, or a mixture containing an organic resin substance in the single substance or composite, or a coated substance coated with the single substance or composite, or an antimony-doped tin oxide and/or tin-doped indium oxide.